

# CHEMICAL COMPOSITIONS

\* Chemical Compositions (JIOU YI Follow JIS G 4308 Standard.)

Material	Chemical Compositions %									
	C	Si	Mn	P	S	Ni	Cr	Mo	Cu	N
SUS 302	0.15 Max	1.00 Max	2.00 Max	0.045 Max	0.030 Max	8.00-10.0	17.0-19.0	-	-	-
SUS 304	0.08 Max	1.00 Max	2.00 Max	0.045 Max	0.030 Max	8.00-10.5	18.0-20.0	-	-	-
SUS 316	0.08 Max	1.00 Max	2.00 Max	0.045 Max	0.030 Max	10.0-14.0	16.0-18.0	2.00-3.00	-	-
SUS 316L	0.03 Max	1.00 Max	2.00 Max	0.045 Max	0.030 Max	12.0-15.0	16.0-18.0	2.00-3.00	-	-

Material	Chemical Compositions %									
	C	Si	Mn	P	S	Ni	Cr	Cu	Al	
SUS 631J1	0.09 Max	1.00 Max	1.00 Max	0.040 Max	0.030 Max	7.00-8.50	16.0-18.0	-	0.75-1.50	

\* Please feel free to contact with us if your company have other request like SUS301 、SUS430...etc.



TEL : +886-3-4193288

FAX : +886-3-4691808

Email : [jiouyiwire@jiouyi.com](mailto:jiouyiwire@jiouyi.com)